

(19)



JAPANESE PATENT OFFICE

## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **11080259 A**(43) Date of publication of application: **26.03.99**

(51) Int. Cl.

**C08F 10/02**  
**B29C 49/00**  
**B65D 1/09**  
**C08L 23/04**  
**C08L 23/08**  
**// B29K 23:00**  
**B29L 22:00**

(21) Application number: **09245217**(22) Date of filing: **10.09.97**(71) Applicant: **TOSOH CORP**(72) Inventor: **KANAZAWA HIDEKI**  
**OGUSU TATSUHIKO**

(54) **POLYETHYLENE RESIN FOR LARGE  
 BLOW-MOLDED PRODUCT, ITS PRODUCTION  
 AND LARGE BLOW-MOLDED CONTAINER**

(57) Abstract:

**PROBLEM TO BE SOLVED:** To obtain a resin desirable for blow-molding large cans for industrial chemicals and containers for use in container trucks or trains by selecting a polyethylene resin specified in a density, a melt flow rate, a molecular weight distribution, a melt tension, a content of boiling n-hexane extractibles and an environmental stress cracking time.

**SOLUTION:** A polyethylene is selected which has a

density of 0.94-0.97 g/cm<sup>3</sup> (JIS K6760-1981), a melt flow rate of 1-15 g/10 min (HLMFR) (JIS K7210-1976, condition 7, at 190°C under a load of 21.8 kg), a weight-average molecular weight/number-average molecular weight (GPC) of 8-15 and a melt tension(MT) of 15-65 g (at 190°C), satisfying the relationship:  
 $\log MT \leq -0.455 \times \log HLMFR + 1.64$  and having a content of boiling n-hexane extractibles of 0.2 wt.% or below and an environmental stress cracking resistance time of 350 hr or above. A large molding made from this resin has excellent low-temperature drop strength and good skin and is capable of long repeated use.

COPYRIGHT: (C)1999,JPO